



Shandong Ningjin Xinxing Chemical Co.,Ltd
 Liaoge Road, Ningjin Industrial, Shandong Province
 Tel: 86-534-5222377
 Fax: 86-534-7074626
 Mobile: 86-13173337240

Data Sheet No: 10521
 Revision: 00
 Effective Date: 8/16/2019
 Page 1 of 2

DATA SHEET			
(Electrically Conductive) UHMW			
Property	Units	Test Method	Typical Average Values
Mechanical			
Specific Gravity, 73° F	-	ASTM D792	.94
Tensile Strength, 73° F	psi	ASTM D638	4800
Tensile Modulus of Elasticity, 73° F	psi	ASTM D638	116000
Tensile Elongation (at break), 73° F	%	ASTM D638	300
Flexural Strength, 73° F	psi	ASTM D790	3100
Flexural Modulus of Elasticity, 73° F	psi	ASTM D790	116000
Shear Strength, 73° F	psi	ASTM D732	
Compressive Strength, 10% Deformation, 73° F	psi	ASTM D695	3300
Compressive Modulus of Elasticity, 73° F	psi	ASTM D695	100000
Hardness, Rockwell, Scale as noted, 73° F	-	ASTM D785	N/A
Hardness, Durometer, Shore "D" Scale, 73° F	-	ASTM D2240	66
Izod Impact (notched), 73° F	ft.lb./in.	ASTM D256 Type "A"	No Break
Coefficient of Friction (Dry vs. Steel) Dynamic	-	QTM 55007	.12
Limiting PV (with 4:1 safety factor applied)	ft.lbs.in. ² min.	QTM 55007	2000
Sand Slurry Abrasion	1018 Steel = 100.	ASTM D4020	10
Thermal			
Coefficient of Linear Thermal Expansion (-40°F to 300°F)	in./in./°F	ASTM E-831 (TMA)	1.1 X 10 ⁻⁴
Heat Deflection Temperature 264 psi	°F	ASTM D648	116
Tg-Glass Transition (amorphous)	°F	ASTM D3418	N/A
Melting Point (crystalline) peak	°F	ASTM D3418	260
Continuous Service Temperature in Air (Max.)(1)	°F	-	180
Thermal Conductivity	BTU in./(hr.ft. ² °F)	-	



Shandong Ningjin Xinxing Chemical Co.,Ltd
 Liaoge Road, Ningjin Industrial, Shandong Province
 Tel: 86-534-5222377
 Fax: 86-534-7074626
 Mobile: 86-13173337240

Data Sheet No: 10521
 Revision: 00
 Effective Date: 8/16/2019
 Page 1 of 2

DATA SHEET			
(Electrically Conductive) UHMW			
Property	Units	Test Method	Typical Average Values
Electrical			
Dielectric Strength, Short Term	Volts/mil	ASTM D149	N/A
Surface Resistivity	ohms/square	ASTM D257	< 10 ⁵
Dielectric Constant, 10 ⁶ Hz	-	ASTM D150	N/A
Dissipation Factor, 10 ⁶ Hz	-	ASTM D150	N/A
Flammability @ 3.1 mm (1/8 in.) (3)	-	UL94	HB
Miscellaneous			
Water Absorption Immersion, 24 Hours	% by wt.	ASTM D570(2)	< 0.01
Water Absorption Immersion, Saturation	% by wt.	ASTM D570(2)	< 0.01

The above data sheet are based on the present knowledge and our present products and are given without guarantee. Different color may have a little difference on the properties.

- 1) Different color have different properties
- 2) Further compositions or approvals on request
- 3) Different additive added depend on the different application

